



# No Hydro Tanking Slurry

## Product Description

No Hydro Tanking Slurry is a cementitious compound designed for application to the surfaces of walls and associated solid floors, which could be subject to penetrating dampness and water ingress.

## Benefits

- Permanent waterproofing
- Easy to use, brush, roller or spray applied
- Resists positive and negative water pressure
- Resists salt contamination in masonry
- Safe to use in contact with potable water
- Use above and below ground level, for internal and external use.

## Properties

Appearance	Grey Powder
Temperature	5 °C – 35 °C
Size(s) & Packaging	20KG Bags
Coverage	Up to 7m <sup>2</sup>
Strength	Superior Bond Strength
Service Life	Permanent
Storage	Store in a cool, dry place in unopened, undamaged original packaging for best use
Shelf Life	12 months

## Application Information

### Preparation

All active water leaks must be stopped using Waterstop (rapid setting plugging compound) before continuing to the next stage of application.

#### Uneven surfaces:

Remove by suitable means, all loose pointing, any remaining render or plaster, wood, dust, grease, oil, organic growth or other foreign materials that may cause contamination or adversely affect adhesion properties. To create a level surface, Universal Mortar should be applied in line with the relevant data sheet, which is available upon request or can be downloaded from our website. Follow the Universal Mortar priming requirements before application.



#### Level Surfaces:

If there is any exposed steel present, apply two coats of suitable corrosion inhibitor to the exposed steel, by brush. Remove all loose material and surface latencies, i.e. dust, oil, grease, corrosion and organic growth, preferably by using wet grit or water blasting techniques. The strength of the concrete subbase must be a minimum of 25 N/mm<sup>2</sup>.

**Note:** Special precautions may be necessary to ensure a continuous waterproof barrier at the wall to floor joints and corner joints. This is to avoid sharp changes of angle in the tanking membrane. The joints should be thoroughly raked out and cleaned prior to an application of Universal Mortar as a fillet seal.

#### Priming:

- Using a brush, roller or spray, apply SBR Latex, mixed 1:1 (by volume) with water.

- Allow to become tacky to the touch. This will take approx. 30 mins to 2 hours.

### Mixing

Tanking Slurry's consistency can be varied to suit the application method

#### Required Water Additions:

Pack Size	20KG
Brush Applied	3.2 - 4 litres
Trowel Applied	3.2 - 3.6 litres
Spray Applied	3.5 - 4.2 litres





When mixing Tanking Slurry, use ONLY CLEAN WATER, a clean mixing vessel and a mechanical mixer.

1. Pour minimum required addition of clean water into the mixing vessel.
2. Using an electric paddle, gradually start to add the powder whilst mixing under low shear to reduce dust generation.
3. Add all powder and increase mixing shear.
4. Mix for approx. 1 - 3 mins to achieve a uniform, lump free slurry.
5. If necessary, gradually add water and mix until desired consistency is achieved. **Do not exceed maximum required water additions as this will result in the product becoming ineffective as a waterproof barrier.**

**Note:** Excessive mechanical mixing should be avoided. Mechanical mixing time must not exceed 5 minutes.

## Application

Tanking Slurry is a minimum 2 coat application, with each layer applied at a uniform thickness of at least 1 mm per coat.

### Brush and trowel applied:

Apply in even layers using a stiff bristled brush or broom/ trowel on vertical surfaces and a rubber squeegee or stiff bristled brush/ trowel for horizontal surfaces. It is essential the first coat is well brushed or trowelled into the surface to ensure a good bond with the substrate.

Allow the first coat to harden (approx. 2 - 5 hours). Apply a second coat of Tanking Slurry as soon as the first coat has hardened, but not fully set.

Apply the second coat at 90° angle to the first, ensuring a minimum overall thickness of 2 mm.

### Spray applied:

Use traditional wet mortar spraying equipment and processes, ensuring final coat provides a uniform thickness of at least 2 mm.

## Conditions & Limitations

The product should not be applied in temperatures under 5°C and falling, or if temperatures are expected to fall below 5°C within 24 hours. Ensure the substrate temperature is not below 5°C before commencing application.

Avoid application in direct sunlight to prevent rapid drying out. If Tanking Slurry dries out too rapidly between coats, repeat priming process. When applying to environments that will contain aquatic life, such as ponds, always finish with Wykamol Technoseal DPM, and refer to the relevant data sheet, which is available upon request or can be downloaded from our website.

**Note:** Gypsum plaster must not be used in direct contact with Tanking Slurry.

## Curing & Ventilation

Curing procedures should be strictly adhered to. It is important that the surface of the slurry is protected from strong sunlight and drying winds, with either a suitable curing compound, polythene sheeting, damp hessian or similar, for a minimum of 48 hours.

If Tanking Slurry will be left unprotected, fine mist spray the surface 3 - 4 times daily, for a minimum of 48 hours.

## Overcoating & Finishing

Tanking Slurry is suitable for overcoating once correctly and thoroughly cured. Plaster should take place using Wykamol's Renovation Plaster, ideally 48 hours after the final coat of Tanking Slurry has been applied.

Repeat priming process as detailed in the substrate preparation section, prior to an application of Renovation Plaster. Refer to relevant data sheet for application instructions, which is available upon request or can be downloaded from our website. If Tanking Slurry has been applied as a DPC, breathable paint must be used on top of any finish. If redecoration is to occur 12 months after the DPC installation, non-breathable finishes may be considered.

However, the moisture content of the plaster and background must be in line with the recommendations of the supplier of the chosen finish.

**Note:** No Hydro Tanking Slurry must not be punctured by wall fixings, e.g. dry lining work etc.

## Health and Safety

For further information and advice, please contact the No Hydro Technical Department and consult the safety data sheet, which is available upon request or can be downloaded from our website.

*The information supplied is in good faith and is based on expertise, experience & usage, however all recommendations are offered without warranty or guarantee, since the usage circumstances are beyond our control. All goods are sold in accordance with Toner Dampproofing Supplies Ltd Conditions of Sale, copies of which are available on request. Customers are advised that products, techniques and / or codes of practice are under constant review and changes occur without notice. You can always download updated information of products, techniques and / or codes of practice at [www.nohydro.co.uk](http://www.nohydro.co.uk)*

